

# AMENDMENTS TO THE CLAIMS

Please cancel claims 3, 7, 15, 16, 18, 37 and 78-82.

Please add new claim 83.

Please amend the claims as follows:

1. (Currently Amended) A monolithic structural catalyst body comprising:  
an outer peripheral wall and  
a plurality of inner partition walls having an average thickness of less than 0.22  
mm,  
the outer peripheral wall and the plurality of inner partition walls having dispersed  
throughout a chemical composition comprising 50-99.9% by weight an inorganic oxide  
composition and at least 0.1% by weight a catalytically active metal functional group  
an inner partition wall having an average thickness of less than 0.22 mm, wherein  
the monolithic structural catalyst body has a hydraulic diameter greater than or equal to  
75 100 mm, and a transverse compressive strength of at least 1.5 kg/cm<sup>2</sup>.
2. (Original) The monolithic structural catalyst body of claim 1, wherein the  
monolithic structural catalyst body has a macroporosity greater than or equal to 0.05 cc/g  
in pores of diameter ranging from 600 to 5,000 Angstroms.
3. (Canceled)
4. (Original) The monolithic structural catalyst body of claim 1, wherein the  
monolithic structural catalyst body comprises a plurality of inner partition walls having  
an average thickness from 0.05 mm to 0.22 mm.
5. (Original) The monolithic structural catalyst body of claim 4, wherein the  
average thickness of the inner partition walls ranges from 0.05 mm to 0.20 mm.
6. (Original) The monolithic structural catalyst body of claim 5, wherein the  
average thickness of the inner partition walls ranges from 0.10 mm to 0.18 mm.

7. (Canceled)
8. (Currently Amended) The monolithic structural catalyst body of claim 7 1, wherein the hydraulic diameter is greater than or equal to 150 mm.
9. (Original) The monolithic structural catalyst body of claim 1, wherein the transverse compressive strength is greater than  $3 \text{ kg/cm}^2$ .
10. (Original) The monolithic structural catalyst body of claim 9, wherein the transverse compressive strength is greater than  $4 \text{ kg/cm}^2$ .
11. (Original) The monolithic structural catalyst body of claim 1, wherein the monolithic structural catalyst body has a defect level of 2% or less.
12. (Original) The monolithic structural catalyst body of claim 1, wherein the monolithic structural catalyst body has a defect level 0.3% or less.
13. (Original) The monolithic structural catalyst body of claim 2, wherein the monolithic structural catalyst body has a defect level of 2% or less.
14. (Original) The monolithic structural catalyst body of claim 2, wherein the monolithic structural catalyst body has a defect level of 0.3% or less.
15. (Canceled)
16. (Canceled)

17. (Currently Amended) A monolithic structural catalyst body comprising:  
an outer peripheral wall and  
a plurality of inner partition walls having an average thickness of less than 0.22  
mm,  
the outer peripheral wall and the plurality of inner partition walls having dispersed  
throughout a chemical composition comprising 50-99.9% by weight an inorganic oxide  
composition and at least 0.1% by weight a catalytically active metal functional group,  
~~an inner partition wall having an average thickness of less than 0.22 mm; and~~  
~~a uniform chemical composition comprising 50-99.9% by weight an inorganic~~  
~~oxide composition and at least 0.1% by weight a catalytically active metal functional~~  
~~group;~~  
wherein the monolithic structural catalyst body has a macroporosity greater than  
or equal to 0.05 cc/g in pores of diameter ranging from 600 to 5,000 Angstroms.
18. (Canceled)
19. (Original) The monolithic structural catalyst body of claim 17, wherein the  
monolithic structural catalyst body has a transverse compressive strength of at least 1.5  
kg/cm<sup>2</sup>.
20. (Original) The monolithic structural catalyst body of claim 17, wherein the  
monolithic structural body comprises a plurality of inner partition walls having an  
average thickness from 0.05 mm to 0.22 mm.
21. (Original) The monolithic structural catalyst body of claim 20, wherein the  
average thickness of the inner partition walls ranges from 0.05 mm to 0.20 mm.
22. (Original) The monolithic structural catalyst body of claim 21, wherein the  
average thickness of the inner partition walls ranges from 0.10 mm to 0.18 mm.

23. (Currently Amended) The monolithic structural catalyst body of claim ~~48~~ 17, wherein the hydraulic diameter is greater than or equal to 100 mm.
24. (Original) The monolithic structural catalyst body of claim 23, wherein the hydraulic diameter is greater than or equal to 150 mm.
25. (Original) The monolithic structural catalyst body of claim 19, wherein the transverse compressive strength is greater than  $3 \text{ kg/cm}^2$ .
26. (Original) The monolithic structural catalyst body of claim 25, wherein the transverse compressive strength is greater than  $4 \text{ kg/cm}^2$ .
27. (Original) The monolithic structural catalyst body of claim 17, wherein the monolithic structural catalyst body has a defect level of 2% or less.
28. (Original) The monolithic structural catalyst body of claim 17, wherein the monolithic structural catalyst body has a defect level of 0.3% or less.
29. (Currently Amended) The monolithic structural catalyst body of claim ~~48~~ 23, wherein the monolithic structural catalyst body has a defect level of 2% or less.
30. (Currently Amended) The monolithic structural catalyst body of claim ~~48~~ 23, wherein the monolithic structural catalyst body has a defect level of 0.3% or less.
31. (Original) The monolithic structural catalyst body of claim 19, wherein the monolithic structural catalyst body has a defect level of 2% or less.
32. (Original) The monolithic structural catalyst body of claim 19, wherein the monolithic structural catalyst body has a defect level of 0.3% or less.

33. (Currently Amended) A monolithic structural catalyst body comprising:  
an outer peripheral wall and  
a plurality of inner partition walls having an average thickness of less than 0.22  
mm,  
the outer peripheral wall and the plurality of inner partition walls having dispersed  
throughout a chemical composition comprising 50-99.9% by weight an inorganic oxide  
composition and at least 0.1% by weight a catalytically active metal functional group  
an inner partition wall having an average thickness of less than 0.22 mm;  
wherein the monolithic structural catalyst body has a hydraulic diameter greater  
than or equal to ~~75~~ 100 mm and a macroporosity greater than or equal to 0.05 cc/g in  
pores of diameter ranging from 600 to 5,000 Angstroms.
34. (Original) The monolithic structural catalyst body of claim 33, wherein the  
monolithic structural body comprises a plurality of inner partition walls having an  
average thickness from 0.05 mm to 0.22 mm.
35. (Original) The monolithic structural catalyst body of claim 34, wherein the  
average thickness of the inner partition walls ranges from 0.05 mm to 0.20 mm.
36. (Original) The monolithic structural catalyst body of claim 35, wherein the  
average thickness of the inner partition walls ranges from 0.10 mm to 0.18 mm.
37. (Canceled)
38. (Currently Amended) The monolithic structural catalyst body of claim ~~37~~ 33,  
wherein the hydraulic diameter is greater than or equal to 150 mm.
39. (Original) The monolithic structural catalyst body of claim 33, wherein the  
monolithic structural catalyst body has a defect level of 2% or less.

40. (Original) The monolithic structural catalyst body of claim 33, wherein the monolithic structural catalyst body has a defect level of 0.3% or less.
41. (Currently Amended) A monolithic structural catalyst body comprising:  
an outer peripheral wall and  
a plurality of inner partition walls having an average thickness of less than 0.22 mm,  
the outer peripheral wall and the plurality of inner partition walls having dispersed throughout a chemical composition comprising 50-99.9% by weight an inorganic oxide composition and at least 0.1% by weight a catalytically active metal functional group,  
an inner partition wall having an average thickness of less than 0.22 mm; and  
a uniform chemical composition comprising 50-99.9% by weight an inorganic oxide composition and at least 0.1% by weight a catalytically active metal functional group;  
 wherein the monolithic structural catalyst body has a hydraulic diameter greater than or equal to ~~75~~ 100 mm.
42. (Original) The monolithic structural catalyst body of claim 41, wherein the monolithic structural catalyst body has a transverse compressive strength of at least 1.5 kg/cm<sup>2</sup>.
43. (Original) The monolithic structural catalyst body of claim 41, wherein the monolithic structural body comprises a plurality of inner partition walls having an average thickness from 0.05 mm to 0.22 mm.
44. (Original) The monolithic structural catalyst body of claim 43, wherein the average thickness of the inner partition walls ranges from 0.05 mm to 0.20 mm.
45. (Original) The monolithic structural catalyst body of claim 44, wherein the average thickness of the inner partition walls ranges from 0.10 mm to 0.18 mm.

46. (Original) The monolithic structural catalyst body of claim 42, wherein the transverse compressive strength is greater than  $3 \text{ kg/cm}^2$ .
47. (Original) The monolithic structural catalyst body of claim 46, wherein the transverse compressive strength is greater than  $4 \text{ kg/cm}^2$ .
48. (Original) The monolithic structural catalyst body of claim 41, wherein the monolithic structural catalyst body has a defect level of 2% or less.
49. (Original) The monolithic structural catalyst body of claim 41, wherein the monolithic structural catalyst body has a defect level of 0.3% or less.
50. (Original) The monolithic structural catalyst body of claim 42, wherein the monolithic structural catalyst body has a defect level of 2% or less.
51. (Original) The monolithic structural catalyst body of claim 42, wherein the monolithic structural catalyst body has a defect level of 0.3% or less.
52. (Currently Amended) A monolithic structural catalyst body comprising:  
an outer peripheral wall and  
a plurality of inner partition walls having an average thickness of less than 0.22 mm,  
the outer peripheral wall and the plurality of inner partition walls having dispersed throughout a chemical composition comprising 50-99.9% by weight an inorganic oxide composition and at least 0.1% by weight a catalytically active metal functional group,  
an inner partition wall having an average thickness of less than 0.22 mm; and  
a uniform chemical composition comprising 50-99.9% by weight an inorganic oxide composition and at least 0.1% by weight a catalytically active metal functional group;  
wherein the monolithic structural catalyst body has a transverse compressive strength of at least  $1.5 \text{ kg/cm}^2$ .

53. (Original) The monolithic structural catalyst body of claim 52, wherein the monolithic structural body comprises a plurality of inner partition walls having an average thickness from 0.05 mm to 0.22 mm.
54. (Original) The monolithic structural catalyst body of claim 53, wherein the average thickness of the inner partition walls ranges from 0.05 mm to 0.20 mm.
55. (Original) The monolithic structural catalyst body of claim 54, wherein the average thickness of the inner partition walls ranges from 0.10 mm to 0.18 mm.
56. (Original) The monolithic structural catalyst body of claim 52, wherein the transverse compressive strength is greater than 3 kg/cm<sup>2</sup>.
57. (Original) The monolithic structural catalyst body of claim 56, wherein the transverse compressive strength is greater than 4 kg/cm<sup>2</sup>.
58. (Original) The monolithic structural catalyst body of claim 52, wherein the monolithic structural catalyst body has a defect level of 2% or less.
59. (Original) The monolithic structural catalyst body of claim 52, wherein the monolithic structural catalyst body has a defect level of 0.3% or less.
60. (Currently Amended) A monolithic structural catalyst body comprising:  
an outer peripheral wall and  
a plurality of inner partition walls having an average thickness of less than 0.22  
mm,  
the outer peripheral wall and the plurality of inner partition walls having dispersed  
throughout a chemical composition comprising 50-99.9% by weight an inorganic oxide  
composition and at least 0.1% by weight a catalytically active metal functional group,  
an inner partition wall having an average thickness of less than 0.22 mm;



wherein the monolithic structural catalyst body has a transverse compressive strength of at least  $1.5 \text{ kg/cm}^2$  and a macroporosity of greater than or equal to  $0.05 \text{ cc/g}$  in pores of diameter ranging from 600 to 5,000 Angstroms.

61. (Original) The monolithic structural catalyst body of claim 60, wherein the monolithic structural body comprises a plurality of inner partition walls having an average thickness from 0.05 mm to 0.22 mm.

62. (Original) The monolithic structural catalyst body of claim 61, wherein the average thickness of the inner partition walls ranges from 0.05 mm to 0.20 mm.

63. (Original) The monolithic structural catalyst body of claim 62, wherein the average thickness of the inner partition walls ranges from 0.10 mm to 0.18 mm.

64. (Original) The monolithic structural catalyst body of claim 60, wherein the transverse compressive strength is greater than  $3 \text{ kg/cm}^2$ .

65. (Original) The monolithic structural catalyst body of claim 60, wherein the transverse compressive strength is greater than  $4 \text{ kg/cm}^2$ .

66. (Original) The monolithic structural catalyst body of claim 60, wherein the monolithic structural catalyst body has a defect level of 2% or less.

67. (Original) The monolithic structural catalyst body of claim 60, wherein the monolithic structural catalyst body has a defect level of 0.3% or less.

68. (Currently Amended) A monolithic structural catalyst body comprising:  
an outer peripheral wall and  
a plurality of inner partition walls having an average thickness of less than 0.22  
mm.

the outer peripheral wall and the plurality of inner partition walls having dispersed throughout a chemical composition comprising 50-99.9% by weight an inorganic oxide composition and at least 0.1% by weight a catalytically active metal functional group,

an inner partition wall having an average thickness of less than 0.22 mm; the monolithic structural catalyst body having at least two of the following characteristics:

a hydraulic diameter greater than or equal to ~~75~~ 100 mm;

a transverse compressive strength of at least 1.5 kg/cm<sup>2</sup>; or

a macroporosity greater than or equal to 0.05 cc/g in pores of diameter ranging from 600 to 5,000 Angstroms; or

a uniform chemical composition comprising 50-99.9% by weight an inorganic oxide composition and at least 0.1% by weight a catalytically active metal functional group; and

further comprising additional deposited catalytic material deposited on at least one of the outer peripheral wall and the plurality of inner partition walls.

69. (Currently Amended) The monolithic structural catalyst body of claim 1 further comprising additional ~~deposited~~ catalytic material deposited on at least one of the outer peripheral wall and the plurality of inner partition walls.

70. (Currently Amended) The monolithic structural catalyst body of claim 17 further comprising additional ~~deposited~~ catalytic material deposited on at least one of the outer peripheral wall and the plurality of inner partition walls.

71. (Currently Amended) The monolithic structural catalyst body of claim 33 further comprising additional ~~deposited~~ catalytic material deposited on at least one of the outer peripheral wall and the plurality of inner partition walls.

72. (Currently Amended) The monolithic structural catalyst body of claim 41 further comprising additional ~~deposited~~ catalytic material deposited on at least one of the outer peripheral wall and the plurality of inner partition walls.

73. (Currently Amended) The monolithic structural catalyst body of claim 52 further comprising additional ~~deposited~~ catalytic material deposited on at least one of the outer peripheral wall and the plurality of inner partition walls.

74. (Currently Amended) The monolithic structural catalyst body of claim 60 further comprising additional ~~deposited~~ catalytic material deposited on at least one of the outer peripheral wall and the plurality of inner partition walls.

75. (Currently Amended) A monolithic structural catalyst body comprising:  
an outer peripheral wall and  
a plurality of inner partition walls having an average thickness of less than 0.22 mm,  
the outer peripheral wall and the plurality of inner partition walls having dispersed throughout a chemical composition comprising 50-99.9% by weight an inorganic oxide composition and at least 0.1% by weight a catalytically active metal functional group,  
~~an inner partition wall having an average thickness of less than 0.22 mm,~~ wherein the monolithic structural catalyst body has a hydraulic diameter greater than or equal to 75 100 mm; and a transverse compressive strength of at least 1.5 kg/cm<sup>2</sup>, ~~and a uniform chemical composition comprising 50-99.9% by weight an inorganic oxide composition and at least 0.1% by weight a catalytically active metal functional group;~~ and wherein the monolithic structural catalyst body further comprises additional deposited catalytic material.

76. (Original) The monolithic structural catalyst body of claim 68, wherein the monolithic structural catalyst body has a defect level of 2% or less.

77. (Original) The monolithic structural catalyst body of claim 68, wherein the monolithic structural catalyst body has a defect level of 0.3% or less.

Claims 78-82 (Canceled)

83. (New) A monolithic structural catalyst body comprising:

an outer peripheral wall and

a plurality of inner partition walls having an average thickness of less than 0.22 mm,

the outer peripheral wall and the plurality of inner partition walls having dispersed throughout a chemical composition comprising 50-99.9% by weight an inorganic oxide composition and at least 0.1% by weight a catalytically active metal functional group,

wherein the monolithic structural catalyst body has a hydraulic diameter greater than or equal to 150  $\mu\text{m}$ , a transverse compressive strength of at least 1.5  $\text{kg/cm}^2$  and a macroporosity greater than or equal to 0.05 cc/g in pores of diameter ranging from 600 to 5,000 Angstroms.